

# SILT FENCE

Unbacked

## Type A – Unbacked Silt Fence

Woven polypropylene geotextile attached to 2" nominal x 2" nominal x 48" hardwood posts (5 staples per post) placed on 6' centers. Custom stake spacing available upon request.

Property	Test Procedure	American Standard
Style (gsm)		100 gsm
Weave		11 x 11 weave
Grab Tensile (lb)	ASTM D-4632	135 x 125
Grab Elongation (%)	ASTM D-4632	15
Mullen Burst (psi)	ASTM D-3786	200 psi
Puncture (lbs)	ASTM D-4833	50 lbs
Trapezoid Tear (lbs)	ASTM D-4533	60 lbs
AOS (sieve)	ASTM D-4751	30 sieve
Flow Rate (gal/min/ft)	ASTM D-4491	20
Permittivity (sec)	ASTM D-4491	0.1 sec
UV Resistance (%/hrs)	ASTM D-4355	80% @ 500 hrs
Roll Width (ft)		3 ft x 100 ft

\* Values above may have a tolerance of +/- 5%

Unless otherwise noted, this specification is based on testing conducted by an independent testing laboratory. The information presented herein, is to the best of our knowledge, true and accurate. No warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe on any patent.



**For more information about materials from Erosion Supply,  
contact inside sales at 865-673-3427 or visit us on the web at  
[www.erosionsupplytn.com](http://www.erosionsupplytn.com)**

**Erosion  
Supply**